

# AMERCOAT® 370

## DESCRIPTION

Two-component, fast dry multi-purpose epoxy coating

## PRINCIPAL CHARACTERISTICS

- Multi-purpose high build epoxy
- Application over a wide range of surface temperatures
- Suitable for immersion in fresh and salt water
- Class A slip resistance for high strength bolted connections

## COLOR AND GLOSS LEVEL

- White, Black, Oxide Red, Light Buff, Pearl Gray
- Flat

Note: Epoxy coatings will characteristically chalk and fade upon exposure to sunlight. Light colors are prone to ambering to some extent

## BASIC DATA AT 68°F (20°C)

Data for mixed product	
Number of components	Two
Volume solids	66 ± 2%
VOC (Supplied)	max. 2.5 lb/US gal (approx. 300 g/l)
Temperature resistance (Continuous)	To 200°F (93°C)
Temperature resistance (Intermittent)	To 250°F (121°C)
Recommended dry film thickness	4.0 - 6.0 mils (100 - 150 µm) depending on system
Theoretical spreading rate	212 ft <sup>2</sup> /US gal for 5.0 mils (5.3 m <sup>2</sup> /l for 125 µm)
Shelf life	Base: at least 36 months when stored cool and dry Hardener: at least 24 months when stored cool and dry

### Notes:

- See ADDITIONAL DATA – Overcoating intervals
- See ADDITIONAL DATA – Curing time
- Intermittent temperature resistance should be less than 5% of the time, and maximum 24 hours
- Color will drift at elevated temperatures

# AMERCOAT® 370

## RECOMMENDED SUBSTRATE CONDITIONS AND TEMPERATURES

- Coating performance is, in general, proportional to the degree of surface preparation
- Abrasive blasting is usually the most effective and economical method. When this is impossible or impractical, coating can be applied over mechanically cleaned surfaces
- All surfaces must be clean, dry and free of all contaminants, including salt deposits. Contact PPG for maximum allowable salt containment levels

---

### Mild steel

- Remove all loose rust, dirt, grease or other contaminants by one of the following depending on the degree of cleanliness required: SSPC SP-2, 3, 6, 7 or 10 (ISO 8501-1 St-2, St-3, Sa 1, Sa 2.5). These minimum surface preparation standards apply to steel that has been previously abrasive blasted. The choice of surface preparation will depend on the system selected and end-use service conditions
- For more severe service and immersion, clean to SSPC SP-10 (ISO8501-1 Sa 2.5). Blast to achieve an anchor profile of 2.0 – 4.0 mils (50 – 100 µm) as indicted by a Keane-Tator Surface profile Comparator or Testex Tape. Previously blasted steel may be ultra-high pressure water jetted to SSPC SP WJ-2(L) / NACE WJ-2(L). The wet surface can be dried by blowing with dry compressed air giving special attention to horizontal surfaces and recesses

---

### Concrete

- Prepare in accordance with SSPC SP-13 guidelines
- Abrade surface per ASTM D-4259 to remove all efflorescence and laitance, to expose subsurface voids, and to provide a surface roughness equivalent of 60 grit sandpaper or coarser
- Test for moisture by conducting a plastic sheet test in accordance with ASTM D4263
- Fill voids as necessary with AMERCOAT 114 A epoxy filler

---

### Galvanized steel

- Remove oil or soap film with detergent or emulsion cleaner
- Lightly abrasive blast with a fine abrasive in accordance with SSPC SP-16 guidelines to achieve a profile of 1.5 – 3.0 mils (38 – 75 µm). When light abrasive blasting is not possible, galvanizing can be treated with a suitable zinc phosphate conversion coating.
- Galvanizing that has at least 12 months of exterior weathering and has a rough surface with white rust present may be over-coated after power washing and cleaning to remove white rust and other contaminants
- The surface must have a measurable profile
- A test patch is recommended to determine compatibility and adhesion
- Not recommended over chromate sealed galvanizing without blasting to thoroughly remove chromates. Adhesion problems may occur

---

### Non-ferrous metals and stainless steel

- Abrasive blast in accordance with SSPC SP-16 guidelines to achieve a uniform and dense 1.5-4.0 mil anchor profile. Size and hardness of abrasive should be adjusted as necessary based on the hardness of the substrate
- Aluminum may be treated with a surface treatment compliant with Mil-DTL-5541 or equivalent (non-immersion applications only).



# AMERCOAT® 370

## Aged coatings

- All surfaces must be clean, dry, tightly bonded and free of all loose paint, corrosion products or chalky residue
  - Abrade surface, or clean with PREP 88. This product is compatible over most types of properly applied and tightly adhering coatings, however, a test patch is recommended to confirm compatibility
- 

## Repair

- Prepare damaged areas to original surface preparation specifications, feathering edges of intact coating. Thoroughly remove dust or abrasive residue before touch-up.
- 

## Substrate temperature and application conditions

- Surface temperature during application should be between 20°F (-7°C) and 120°F (49°C)
  - Surface temperature during application should be at least 5°F (3°C) above dew point
  - Ambient temperature during application and curing should be between 20°F (-7°C) and 120°F (49°C)
  - Relative humidity during application should not exceed 85%
- 

## **SYSTEM SPECIFICATION**

- Primers: Direct to substrate; DIMETCOTE- Series Primers, AMERCOAT 68HS, AMERCOAT 68MCZ
  - Topcoats: AMERCOAT 450-Series Polyurethanes, AMERSHIELD, PSX 700, AMERCOAT 229T, PITTHANE Polyurethanes
- 

## **INSTRUCTIONS FOR USE**

### Mixing ratio by volume: base to hardener 80:20 (4:1)

- Pre-mix base component with a pneumatic air mixer at moderate speeds to homogenize the container. Add hardener to base and agitate with a power mixer for 1–2 minutes until completely dispersed
- 

### Induction time

None

---

### Pot life

4 hours at 70°F (21°C)

Note: See ADDITIONAL DATA – Pot life

---

# AMERCOAT® 370

---

## **Application**

- Area should be sheltered from airborne particulates and pollutants
- Avoid combustion gases or other sources of carbon dioxide that may promote amine blush and ambering of light colors
- Ensure good ventilation during application and curing
- Provide shelter to prevent wind from affecting spray patterns

## **Material temperature**

Material temperature during application should be between 40°F (4°C) and 90°F (32°C)

---

## **Air spray**

- Use standard conventional equipment

## **Recommended thinner**

THINNER 21-06 (AMERCOAT 65) (xylene), THINNER 21-25 (AMERCOAT 101) (recommended for > 90°F (32°C))

## **Volume of thinner**

0 - 20%

## **Nozzle orifice**

Approx. 0.070 in (1.8 mm)

---

## **Airless spray**

- 45:1 pump or larger
- Can be applied with plural component equipment

## **Recommended thinner**

THINNER 21-06 (AMERCOAT 65) (xylene), THINNER 21-25 (AMERCOAT 101) (recommended for > 90°F (32°C))

## **Nozzle orifice**

0.017 – 0.019 in (approx. 0.43 – 0.48 mm)

---

## **Brush/roller**

- Use a high quality natural bristle brush and/or solvent resistant, 3/8" nap roller. Ensure brush/roller is well loaded to avoid air entrainment. Multiple coats may be necessary to achieve adequate film-build

## **Recommended thinner**

AMERCOAT 65 (xylene), AMERCOAT 101 (recommended for > 90°F (32°C))

---

## **Cleaning solvent**

Amercoat 12 Cleaner (Thinner 90-58) or Amercoat 65 Thinner (Thinner 21-06)

# AMERCOAT® 370

## ADDITIONAL DATA

Overcoating interval for DFT up to 4.0 mils (100 µm)						
Overcoating with...	Interval	20°F (-7°C)	32°F (0°C)	50°F (10°C)	70°F (21°C)	90°F (32°C)
urethane and PSX	Minimum	3 hours	2 hours	1.5 hours	45 minutes	30 minutes
	Maximum	2 months	1.5 months	1.5 months	30 days	14 days

Notes:

- Surface must be clean and dry. Any contamination must be identified and removed. A detergent wash with PREP 88 or equivalent is required prior to application of topcoats after 30 days of exposure. However, particular attention must be paid to surfaces exposed to sunlight where chalking may be present. In those situations, a further degree of cleaning may be required. PPG Technical Service can advise on suitable cleaning methods. If maximum recoat/topcoat time is exceeded, then roughen surface.
- Dry times are dependent on air and surface temperatures as well as film thickness, ventilation, and relative humidity. Maximum recoating time is highly dependent upon actual surface temperatures – not simply air temperatures. Surface temperatures should be monitored, especially with sun-exposed or otherwise heated surfaces. Higher surface temperatures shorten the maximum recoat window

Overcoating interval for DFT up to 4.0 mils (100 µm)						
Overcoating with...	Interval	20°F (-7°C)	32°F (0°C)	50°F (10°C)	70°F (21°C)	90°F (32°C)
itself	Minimum	3 hours	2 hours	1.5 hours	45 minutes	30 minutes
	Maximum - immersion	3 months	2 months	30 days	30 days	30 days
	Maximum - non-immersion	6 months	6 months	6 months	6 months	6 months

Notes:

- Surface must be clean and dry. Any contamination must be identified and removed. A detergent wash with PREP 88 or equivalent is required prior to application of topcoats after 30 days of exposure. However, particular attention must be paid to surfaces exposed to sunlight where chalking may be present. In those situations, a further degree of cleaning may be required. PPG Technical Service can advise on suitable cleaning methods. If maximum recoat/topcoat time is exceeded, then roughen surface.
- If the surface is uniformly and freely chalking after 6 months of exterior weathering, the surface is recoatable with itself after thorough cleaning.
- Dry times are dependent on air and surface temperatures as well as film thickness, ventilation, and relative humidity. Maximum recoating time is highly dependent upon actual surface temperatures – not simply air temperatures. Surface temperatures should be monitored, especially with sun-exposed or otherwise heated surfaces. Higher surface temperatures shorten the maximum recoat window

Curing time for DFT up to 4.0 mils (100 µm)			
Substrate temperature	Dry to touch	Dry to handle	Service- water immersion
20°F (-7°C)	2 hours	20 hours	N/A
32°F (0°C)	1.5 hours	9 hours	7 days
50°F (10°C)	45 minutes	4.5 hours	48 hours
70°F (21°C)	30 minutes	1.5 hours	24 hours
90°F (32°C)	20 minutes	75 minutes	12 hours

Note: Adequate ventilation must be maintained during application and curing

# AMERCOAT® 370

Pot life (at application viscosity)	
Mixed product temperature	Pot life
50°F (10°C)	6 hours
70°F (21°C)	4 hours
90°F (32°C)	2 hours

## Product Qualifications

- ANSI / NSF Standard 61 for drinking water (valves only). For NSF application instructions, please visit our website at: [www.ppgamercoatus.ppgpmc.com/NSF/](http://www.ppgamercoatus.ppgpmc.com/NSF/)
- AWWA C550-06
- Compliant with USDA Incidental Food Contact Requirements
- Qualified for Class A Slip Resistance per the Research Council on Structural Connections, Appendix A

## SAFETY PRECAUTIONS

- For paint and recommended thinners see INFORMATION SHEETS 1430, 1431 and relevant Material Safety Data Sheets
- This is a solvent-borne paint and care should be taken to avoid inhalation of spray mist or vapor, as well as contact between the wet paint and exposed skin or eyes

## WORLDWIDE AVAILABILITY

It is always the aim of PPG Protective and Marine Coatings to supply the same product on a worldwide basis. However, slight modification of the product is sometimes necessary to comply with local or national rules/circumstances. Under these circumstances an alternative product data sheet is used.

## REFERENCES

• CONVERSION TABLES	INFORMATION SHEET	1410
• EXPLANATION TO PRODUCT DATA SHEETS	INFORMATION SHEET	1411
• SAFETY INDICATIONS	INFORMATION SHEET	1430
• SAFETY IN CONFINED SPACES AND HEALTH SAFETY, EXPLOSION HAZARD – TOXIC HAZARD	INFORMATION SHEET	1431

## WARRANTY

PPG warrants (i) its title to the product, (ii) that the quality of the product conforms to PPG's specifications for such product in effect at the time of manufacture and (iii) that the product shall be delivered free of the rightful claim of any third person for infringement of any U.S. patent covering the product. THESE ARE THE ONLY WARRANTIES THAT PPG MAKES AND ALL OTHER EXPRESS OR IMPLIED WARRANTIES, UNDER STATUTE OR ARISING OTHERWISE IN LAW, FROM A COURSE OF DEALING OR USAGE OF TRADE, INCLUDING WITHOUT LIMITATION, ANY OTHER WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE OR USE, ARE DISCLAIMED BY PPG. Any claim under this warranty must be made by Buyer to PPG in writing within five (5) days of Buyer's discovery of the claimed defect, but in no event later than the expiration of the applicable shelf life of the product, or one year from the date of the delivery of the product to the Buyer, whichever is earlier. Buyer's failure to notify PPG of such non-conformance as required herein shall bar Buyer from recovery under this warranty.

# AMERCOAT® 370

## LIMITATIONS OF LIABILITY

IN NO EVENT WILL PPG BE LIABLE UNDER ANY THEORY OF RECOVERY (WHETHER BASED ON NEGLIGENCE OF ANY KIND, STRICT LIABILITY OR TORT) FOR ANY INDIRECT, SPECIAL, INCIDENTAL, OR CONSEQUENTIAL DAMAGES IN ANY WAY RELATED TO, ARISING FROM, OR RESULTING FROM ANY USE MADE OF THE PRODUCT. The information in this sheet is intended for guidance only and is based upon laboratory tests that PPG believes to be reliable. PPG may modify the information contained herein at any time as a result of practical experience and continuous product development. All recommendations or suggestions relating to the use of the PPG product, whether in technical documentation, or in response to a specific inquiry, or otherwise, are based on data, which to the best of PPG's knowledge, is reliable. The product and related information is designed for users having the requisite knowledge and industrial skills in the industry and it is the end-user's responsibility to determine the suitability of the product for its own particular use and it shall be deemed that Buyer has done so, as its sole discretion and risk. PPG has no control over either the quality or condition of the substrate, or the many factors affecting the use and application of the product. Therefore, PPG does not accept any liability arising from any loss, injury or damage resulting from such use or the contents of this information (unless there are written agreements stating otherwise). Variations in the application environment, changes in procedures of use, or extrapolation of data may cause unsatisfactory results. This sheet supersedes all previous versions and it is the Buyer's responsibility to ensure that this information is current prior to using the product. Current sheets for all PPG Protective & Marine Coatings Products are maintained at [www.ppgpmc.com](http://www.ppgpmc.com). The English text of this sheet shall prevail over any translation thereof.

Packaging: Available in 1-gallon and 5-gallon kits; (1-gallon kits have 0.8 gallons of base and 0.2 gallons of hardener; 5 gallon kits have 4-gallons of base and 1-gallon of hardener)

Product code	Description
AT370-112	Light Buff Base
AT370-3	White Base
AT370-9	Black Base
AT370-23	Pearl Gray Base
AT370-72	Oxide Red Base
AT370-B	Hardener

The PPG Logo, Bringing innovation to the surface., and all other trademarks herein are property of the PPG group of companies.



**PPG Protective &  
Marine Coatings**

Bringing innovation to the surface.™