

KL4400 SERIES

ANODIC SELF-PRIMING PAINT

DESCRIPTION

One-component, alkyd / oil resin, zinc dust

PRINCIPAL CHARACTERISTICS

- Single component, high-build, high solids, rust inhibitive coating designed such that a single coat will provide long term protection
- Excellent corrosion protection properties
- Self Priming in many applications
- High solids, VOC compliant
- Can be applied and dries at temperatures down to 35°F (2°C) as long as temperatures are expected to rise over the following months
- Can be used for painting weathered galvanized or previously painted surfaces of transmission or communication towers, poles, substation structures, chain link fencing, buildings and bridges

COLOR AND GLOSS LEVEL

- Green Gray, gray, and shades of gray
- Flat

BASIC DATA AT 25°C (77°F)

Data for mixed product	
Number of components	One
Volume solids	92 ± 2%
VOC (Supplied)	EPA Method 24: 0.5 lb/US gal (64.7 g/l)
Recommended dry film thickness	6.0 - 10.0 mils (150 - 250 µm) depending on system
Theoretical spreading rate	6.1 m ² /l for 150 µm (245 ft ² /US gal for 6.0 mils)
Dry to touch	24 hours at 25 °C (77°F)
Dry to topcoat	2 months
Dry to handle	3 days
Shelf life	At least 24 months when stored cool and dry

Notes:

- Values are calculated using KL4407, Anodic S/P Gray. Values will vary with color
- Drying times listed may vary depending on temperature, humidity and air movement
- Not recommended for shop application



KL4400 SERIES

ANODIC SELF-PRIMING PAINT

RECOMMENDED SUBSTRATE CONDITIONS AND TEMPERATURES

- For application to steel surfaces
- Can be applied to previously painted surfaces in sound condition
- For application to weathered galvanized surfaces
- Coating performance is, in general, proportional to the degree of surface preparation
- The surface to be coated must be properly prepared, dry, clean and free of contamination. Minimum surface preparation is SSPC-SP2 Hand Tool Cleaning
- LIMITATIONS FOR USE: For professional use only; not intended for household use.

Weathered galvanized steel - Phase I Tower Condition

- Coffee stain rust (cosmetic)
- Approximately 1-2 mils galvanization left

Note: Use SSPC-SP1 then apply 1 coat KL4400 SERIES Anodic Self-Priming Paint (desired color)

Previously painted surfaces in good condition - Phase I Tower Condition

- Coffee stain rust (cosmetic)
- Approximately 5% rust

Note: Use SSPC-SP1 then apply 1 coat KL4400 SERIES Anodic Self-Priming Paint (desired color)

Previously painted surfaces in poor condition with some localized corrosion - Phase II Tower Condition

- Abrasive rust
- On bolts, angles, edges and horizontal flat areas
- Rust falls off when finger touches it

Notes:

- Use SSPC-SP2 or SP3 followed by SSPC-SP1
- Spot prime with KLC2129 Kolor-Poxy Penetrating Sealer
- Spot to Full Primer as needed using either KL6000 Tri-Polar Ferrite Primer or Speedhide 6-208
- Apply 1 coat KL4400 SERIES Anodic Self-Priming Paint (desired color)

Previously painted surfaces in very poor condition with > 35% corrosion - Phase III Tower Condition

- Extensive abrasive rust

Notes:

- Use SSPC-SP2 or SP3 followed by SSPC-SP1
- Severe corrosion may require SSPC-SP6 (contact local PPG PMC sales representative for specific recommendation)
- If abrasive blast preparation is not possible, use SSPC-SP11, power tool cleaning to bare metal (ISO-St3)
- Full prime with KLC2129 Kolor-Poxy Penetrating Sealer
- Full prime using either KL6000 Tri-Polar Ferrite Primer or Speedhide 6-208
- Use SSPC-SP1 then apply 1 coat KL4400 SERIES Anodic Self-Priming Paint (desired color)

KL4400 SERIES

ANODIC SELF-PRIMING PAINT

Substrate temperature

- DONOTUSE Above 130°F (54°C) and below 35°F (2°C), and at least 5°F (3°C) above dew point during application and curing
-

Warning

Removal of old paint by sanding, scraping or other means may generate dust or fumes which contain lead. EXPOSURE TO LEAD DUST OR FUMES MAY CAUSE ADVERSE HEALTH EFFECTS, ESPECIALLY IN CHILDREN OR PREGNANT WOMEN. Controlling exposure to lead or other hazardous substances requires the use of proper protective equipment, such as a properly fitted and approved (e.g., NIOSH approved) respirator and proper containment and cleanup. For additional information, contact the USEPA/Lead Information Hotline at 1-800-424-LEAD or the regional Health Canada office

INSTRUCTIONS FOR USE

- Mix thoroughly before application
 - Mix full units as packaged only. Mix with a heavy duty mud mixer with a 1/2" shaft and suitable power drill.
 - If mechanical mixing is not possible mix the KL4400 SERIES by "Boxing" between two containers at least 10 times or as necessary to assure that the entire container is uniform in consistency and smoothness.
-

Material temperature

If components have been stored above 32°C (90°F), cool between 7°C (45°F) and 32°C (90°F)

Note: Caution - Material stored at elevated temperatures for extended periods of time (in excess of one year) may generate gas internally and cause damage to the container allowing paint to leak out.

Airless spray

- Thin up to 25% by volume with Thinner 20-05 as needed
-

Brush/roller

- Use a high quality natural bristle brush
- Use a 3/8" to 1/2" nap roller with a solvent resistant core
- Application using a "mitt" is an acceptable method and in many cases the preferred method
- Roller application for chain link fencing should be with a long nap type one to one and a half inches deep

Recommended thinner

Thinning is NOT recommended for brush, roller, or mitt application

ADDITIONAL DATA

KL4400 SERIES

ANODIC SELF-PRIMING PAINT

SAFETY PRECAUTIONS

- **DANGER:** Rags, steel wool or waste soaked with this product may spontaneously catch fire if improperly discarded. Immediately after use, place rags, steel wool or waste in a sealed water-filled metal container. Refer to www.hpc.com Spontaneous Combustion Advisory for additional information.
- Animals are attracted to the KL4400 SERIES, therefore empty cans should be disposed of properly and not left at the jobsite. Furthermore, animals should be kept away from freshly painted structures with temporary fencing for 30 days.

WARRANTY

PPG warrants (i) its title to the product, (ii) that the quality of the product conforms to PPG's specifications for such product in effect at the time of manufacture and (iii) that the product shall be delivered free of the rightful claim of any third person for infringement of any U.S. patent covering the product. THESE ARE THE ONLY WARRANTIES THAT PPG MAKES AND ALL OTHER EXPRESS OR IMPLIED WARRANTIES, UNDER STATUTE OR ARISING OTHERWISE IN LAW, FROM A COURSE OF DEALING OR USAGE OF TRADE, INCLUDING WITHOUT LIMITATION, ANY OTHER WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE OR USE, ARE DISCLAIMED BY PPG. Any claim under this warranty must be made by Buyer to PPG in writing within five (5) days of Buyer's discovery of the claimed defect, but in no event later than the expiration of the applicable shelf life of the product, or one year from the date of the delivery of the product to the Buyer, whichever is earlier. Buyer's failure to notify PPG of such non-conformance as required herein shall bar Buyer from recovery under this warranty.

LIMITATIONS OF LIABILITY

IN NO EVENT WILL PPG BE LIABLE UNDER ANY THEORY OF RECOVERY (WHETHER BASED ON NEGLIGENCE OF ANY KIND, STRICT LIABILITY OR TORT) FOR ANY INDIRECT, SPECIAL, INCIDENTAL, OR CONSEQUENTIAL DAMAGES IN ANY WAY RELATED TO, ARISING FROM, OR RESULTING FROM ANY USE MADE OF THE PRODUCT. The information in this sheet is intended for guidance only and is based upon laboratory tests that PPG believes to be reliable. PPG may modify the information contained herein at any time as a result of practical experience and continuous product development. All recommendations or suggestions relating to the use of the PPG product, whether in technical documentation, or in response to a specific inquiry, or otherwise, are based on data, which to the best of PPG's knowledge, is reliable. The product and related information is designed for users having the requisite knowledge and industrial skills in the industry and it is the end-user's responsibility to determine the suitability of the product for its own particular use and it shall be deemed that Buyer has done so, as its sole discretion and risk. PPG has no control over either the quality or condition of the substrate, or the many factors affecting the use and application of the product. Therefore, PPG does not accept any liability arising from any loss, injury or damage resulting from such use or the contents of this information (unless there are written agreements stating otherwise). Variations in the application environment, changes in procedures of use, or extrapolation of data may cause unsatisfactory results. This sheet supersedes all previous versions and it is the Buyer's responsibility to ensure that this information is current prior to using the product. Current sheets for all PPG Protective & Marine Coatings Products are maintained at www.ppgmc.com. The English text of this sheet shall prevail over any translation thereof.

AVAILABILITY

Packaging

5-gallon containers

Product codes	Description
KL4401/05	Green Gray
KL4404/05	Galvanize Gray
KL4404S/05	Galvanize Gray Stainless Steel
KL4407/05	Sky Gray

The PPG Logo, Bringing innovation to the surface., and all other trademarks herein are property of the PPG group of companies.



PPG Protective & Marine Coatings

Bringing innovation to the surface.™